

HyGold P150N

Paraffinic Base Oil Marketing Specification

This severely hydrotreated paraffinic base oil provides excellent color and consistency. It passes the IP 346 labeling requirement.

TEST DESCRIPTION	TEST METHOD	SPECIFICATIONS		TYPICAL VALUES
		MIN	MAX	
Physical Properties				
Viscosity, SUS at 100°F (37.8°C)	ASTM D2161	137	161	150
Viscosity, SUS at 210°F (98.9°C)	ASTM D2161			43.6
Viscosity, cSt at 40°C (104°F)	ASTM D445	26.4	31.2	29.1
Viscosity, cSt at 100°C (212°F)	ASTM D445			5.2
API Gravity, 60°F (15.6°C)	ASTM D1250			33.5
Specific Gravity, 60°F (15.6°C)	ASTM D4052			0.8575
Viscosity Index	ASTM D2270	94		107
Viscosity-Gravity Constant	ASTM D2501			0.801
Density, lbs/gal at 60°F	ASTM D1250			7.146
Density at 15.6°C, g/cm ³	ASTM D1250			0.8568
Molecular Weight	ASTM D2502			401
Flash Point, COC, °F (°C)	ASTM D92	379 (193)		430 (221)
Flash Point, PMCC, °F (°C)	ASTM D93			414 (212)
Color, ASTM	ASTM D6045		1.5	L0.5
Pour Point, °F (°C)	ASTM D5949		18 (-8)	2 (-16)
Cloud Point, °F (°C)	ASTM D5773			7 (-14)
Noack Volatility, wt%	ASTM D5800			16.2
Water Content	ASTM D7546M		PASS	PASS
Appearance	ASTM D4176M		PASS	PASS
Chemical Properties				
Acid Number, mg KOH/g	ASTM D664			0.01
Aniline Point, °F (°C)	ASTM D611	223 (106)	237 (114)	232 (111)
Sulfur, ppm	ASTM D7220			6
Health and Safety Properties				
Polycyclic Aromatic Compounds, wt%	IP 346		3	<3
Modified Ames Assay, MI	ASTM E1687		1	<1
FDA Regulation	21 CFR 178.3620 (C)		PASS	PASS